



HIGH PERFORMANCE CLEAR ACRYLIC INDOOR/OUTDOOR DEAD FLAT

TECHNICAL DATA SHEET

PRODUCT NUMBER

DESCRIPTION

M102-0005,M102-0005JPN	HIGH PERFORMANCE CLEAR ACRYLIC INDOOR/OUTDOOR DEAD FLAT
------------------------	--

PRODUCT DESCRIPTION:

The High Performance Clear Acrylic Aerosol is made with high-quality non-yellowing acrylic resins. This aerosol was formulated to adhere wood, metal, powder coating, catalyzed coatings, and other materials. The perfect choice for all your indoor and outdoor projects.

ADVANTAGES:

- Superior flow out and blending
- Great clarity and durability
- Non-yellowing
- Excellent atomization
- Excellent adhesion

PHYSICAL PROPERTIES AND SPECIFICATIONS

Technology	ACRYLIC LACQUER
Color	clear
Sheen	Dead Flat 3° ± 2°
Viscosity	N/A
WPG	6.515851112 lbs/gal
Solids by Volume	6.372822809 ±1%
Solids by Weight	9.525544028 ±1%
Flash Point	-76.000000000 °F
HMIS	H: 2, F: 4, R: 0, P: X
Coating VOC (g/l)	611.746084052 g/l
Coating VOC (Lb/Gal)	5.105286699 lbs/gal
Material VOC (g/l)	382.997599699 g/l
Material VOC (Lb/Gal)	3.196281272 lbs/gal
#VOC/#Solid	5.149725139 lbs/lbs solid
VHAP Ratio (#VHAP/#Solid)	0.502774410
Spread Rate	102.220077856 sq. ft./gal @ 1.0 mil DFT (no loss)
Catalyst/Ratio	N/A
Reducer	N/A
Retarder	N/A
AirDry	To touch: 7 minutes; To handle: 15 minutes; To package: overnight
Oven Dry	N/A
Shelf-Life (Unopened)	36 months
Pot-Life (Catalyzed)	N/A
Recoat Instruction	Dry 30 to 45 minutes; scuff sand between coats with 320 grit or equivalent
PH	N/A

DIRECTIONS:

DIRECTIONS: Clean surface to be sprayed with Mohawk Wax Wash™ Remover. For best results, can temperature should be 65° - 90°. SHAKE WELL BEFORE USING for at least one minute after the ball rattles to ensure uniform mixing. Point opening of spray button toward object, holding can 12 to 14 inches away from surface to be coated. Press spray button firmly. Use steady, even strokes. Several thin coats give a better finish than one heavy coat. Allow coating to become dry to the touch between coats. Clean spray button immediately by spraying with the can upside down until no product comes out. Allow coating to dry for at least 24 hours before placing outdoors.

The data on this sheet are calculated values (as formulated) and will not represent exact values for every product. For Safety and Other Precautions, read the SDS before using the product. SDS are available upon request. If Safety Data Sheet is required, contact: Mohawk Finishing Products, a Division of RPM Industrial Coatings Group, Inc.; 3194 B Hickory Blvd, Hudson, NC 28638; Phone: 1-800-545-0047; Fax: 1-800-721-1545.

Drying times and viscosities reported are as tested under laboratory conditions (77°F (25°C)) with relative humidity of approximately 45%. Changes in temperature and humidity will affect product data.

It is the user's responsibility to verify product compliance with all applicable regulations or permits before proceeding with use. Always pretest any finishing products to verify suitability to the desired use before proceeding with any application. Manufacturer makes no warranties, express or implied, including (but not limited to) warranties of merchantability and fitness for particular purposes. Manufacturer will not be liable for any incidental, consequential or special damages or losses derived, directly or indirectly, from or as a consequence of purchaser's use of this product.

TDS. Mohawk Finishing Products, Division of RPM Wood Finishes Group, Inc. All rights reserved.