



# NO BLUSH™ RETARDER 1GAL

## TECHNICAL DATA SHEET

PRODUCT NUMBER	DESCRIPTION
FE200-013-1,M716-2407	NO BLUSH™ RETARDER 1GAL

### PRODUCT DESCRIPTION:

No Blush™ Retarder is a blend of slow evaporating solvents to be used with all nitrocellulose, pre-catalyzed lacquer and post-catalyzed lacquer coatings. Small amounts may be added to correct most flow, blushing or leveling problems that are often seen during application in humid environments.

### ADVANTAGES:

1. Prevent blushing
2. Enhance flow
3. Improves gloss and leveling

### PHYSICAL PROPERTIES AND SPECIFICATIONS

Technology	Solvent Reducer/Retarder
Color	N/A
Sheen	N/A
Viscosity	N/A
WPG	7.104887143 lbs/gal
Solids by Volume	0.004231732 ±1%
Solids by Weight	0.005000000 ±1%
Flash Point	-4.000000000 °F
HMIS	H: 2, F: 3, R: 0, P: X
Coating VOC (g/l)	865.403171093 g/l
Coating VOC (Lb/Gal)	7.222165232 lbs/gal
Material VOC (g/l)	681.037597922 g/l
Material VOC (Lb/Gal)	5.683554470 lbs/gal
#VOC/#Solid	15999.016085592 lbs/lbs solid
VHAP Ratio (#VHAP/#Solid)	4000.004021461
Spread Rate	0.067876981 sq. ft./gal @ 1.0 mil DFT (no loss)
Catalyst/Ratio	N/A
Reducer	N/A
Retarder	N/A
AirDry	N/A
Oven Dry	N/A
Shelf-Life (Unopened)	36 months
Pot-Life (Catalyzed)	N/A
Recoat Instruction	N/A
PH	N/A

Not for use in waterbase products.

### DIRECTIONS:

DIRECTIONS: Add as needed in small increments, up to 10% by volume, to correct issues. NOTES: No Blush™ Retarder will extend dry time. Exercise caution to not add more than is needed to correct the issue. Not for use with Conversion Varnish coatings.

*The data on this sheet are calculated values (as formulated) and will not represent exact values for every product. For Safety and Other Precautions, read the SDS before using the product. SDS are available upon request. If Safety Data Sheet is required, contact: Mohawk Finishing Products, a Division of RPM Industrial Coatings Group, Inc.; 3194 B Hickory Blvd, Hudson, NC 28638; Phone: 1-800-545-0047; Fax: 1-800-721-1545.*

*Drying times and viscosities reported are as tested under laboratory conditions (77°F (25°C)) with relative humidity of approximately 45%. Changes in temperature and humidity will affect product data.*

*It is the user's responsibility to verify product compliance with all applicable regulations or permits before proceeding with use. Always pretest any finishing products to verify suitability to the desired use before proceeding with any application. Manufacturer makes no warranties, express or implied, including (but not limited to) warranties of merchantability and fitness for particular purposes. Manufacturer will not be liable for any incidental, consequential or special damages or losses derived, directly or indirectly, from or as a consequence of purchaser's use of this product.*

TDS. Mohawk Finishing Products, Division of RPM Wood Finishes Group, Inc. All rights reserved.