



ENDURAGREEN® EXTERIOR CLEAR URETHANE 80 SHEEN

TECHNICAL DATA SHEET

PRODUCT NUMBER

DESCRIPTION

A29C4280OHAW,
A29C4280WP5S

ENDURAGREEN® EXTERIOR CLEAR
URETHANE 80 SHEEN

PHYSICAL PROPERTIES AND SPECIFICATIONS

Technology	WATERBORNE URETHANE
Color	CLEAR
Sheen	80 +/- 3 SHEEN AT 5 WET MILS APPLIED
Viscosity	30 +/-2 #3 SIGNATURE ZAHN CUP
WPG	8.69 lbs/gal
Solids by Volume	34.24 ±1%
Solids by Weight	36.89 ±1%
Flash Point	0.00 °F
HMIS	H: 2, F: 1, R: 0, P: X
Coating VOC (g/l)	100.81 g/l
Coating VOC (Lb/Gal)	0.84 lbs/gal
Material VOC (g/l)	38.84 g/l
Material VOC (Lb/Gal)	0.32 lbs/gal
#VOC/#Solid	0.10 lbs/lbs solid
VHAP Ratio (#VHAP/#Solid)	0.08
Spread Rate	549.28 sq. ft./gal @ 1.0 mil DFT (no loss)
Catalyst/Ratio	N/A
Reducer	WATER
Retarder	PROPYLENE GLYCOL IF NEEDED / 2-3 OZ PER GALLON
Air Dry	45 MINUTES TO HANDLE AT ROOM TEMP, 2 HOURS TO SAND
Oven Dry	N/A
Shelf-Life (Unopened)	12 months
Pot-Life (Catalyzed)	N/A
Recoat Instruction	DRY AT LEAST 2 HOURS, SCUFF SAND PRIOR TO RECOAT
PH	N/A
Contains UV Absorber	
Maximum dry film thickness for total system not to exceed 4 dry mils	

The data on this sheet are calculated values (as formulated) and will not represent exact values for every product. SDS and CPDS sheets are available upon request. Drying times and viscosities reported are as tested under laboratory conditions (77°F (25°C) with relative humidity of approximately 45%. Changes in temperature and humidity will affect product data. The following definitions are being utilized for HAP content: "HAPS-Compliant": < or = .8 lb. HAPS/Lb. Solids; "Low-HAPS": <.5 Lb. HAPS/Lb. Solids; "Ultra-Low-HAPS": <.2 Lb. HAPS/Lb. Solids; "HAPS-Free": <0.00 Lb. HAPS/Lb. Solids. HAP content is based upon the presence of HAP compounds utilizing limits as defined in 29 CFR 1910.1200. Manufacturer assumes no liability for use of this information which is intended to serve as a general guide.

It is the user's responsibility to verify product compliance with all applicable regulations or permits before proceeding with use. Always pretest any finishing products to verify suitability to the desired use before proceeding with any application. Manufacturer makes no warranties, express or implied, including (but not limited to) warranties of merchantability and fitness for particular purposes. Manufacturer will not be liable for any incidental, consequential or special damages or losses derived, directly or indirectly, from or as a consequence of purchaser's use of this product.

TDS. Finishworks™, Division of RPM Industrial Coatings Group, Inc. All rights reserved.