



ULTRA FLO CLEAR CONVERSION VARNISH SATIN 40 SHEEN GAL

TECHNICAL DATA SHEET

| PRODUCT NUMBER | DESCRIPTION |
|----------------|---|
| M615-21407 | ULTRA FLO CLEAR CONVERSION VARNISH SATIN 40 SHEEN GAL |

PRODUCT DESCRIPTION:

Mohawk Ultra® Flo Clear Conversion Varnish is a conventional VOC, clear, non-yellowing, catalyzed coating for cabinetry, millwork and other interior wood surfaces where maximum durability and moisture protection is needed. Ultra® Flo Clear Conversion Varnish may be used as a self-sealing system or over Mohawk E-Z Vinyl® Sealer (M610-800) or Ultra® Clear Conversion Varnish Sealer (M615-2900).

ADVANTAGES:

- 1 High moisture and chemical resistance, meets all KCMA test requirements
- 2 Non-yellowing, UV inhibitor
- 3 Excellent cold check resistance
- 4 Excellent adhesion

PHYSICAL PROPERTIES AND SPECIFICATIONS

| | |
|---------------------------|---|
| Technology | Solvent based conversion varnish |
| Color | Clear when dry |
| Sheen | 40° ±2 |
| Viscosity | 39" ±1; Zahn #1 sig @ 77° F |
| WPG | 7.760960943 lbs/gal |
| Solids by Volume | 32.955188679 ±1% |
| Solids by Weight | 39.259987463 ±1% |
| Flash Point | 39.200000000 °F |
| HMIS | H: 2, F: 3, R: 0, P: X |
| Coating VOC (g/l) | 564.541469418 g/l |
| Coating VOC (Lb/Gal) | 4.711343694 lbs/gal |
| Material VOC (g/l) | 564.121009509 g/l |
| Material VOC (Lb/Gal) | 4.707834773 lbs/gal |
| #VOC/#Solid | 1.545096319 lbs/lbs solid |
| VHAP Ratio (#VHAP/#Solid) | 0.345190610 |
| Spread Rate | 528.601226411 sq. ft./gal @ 1.0 mil DFT (no loss) |
| Catalyst/Ratio | M615-701X; 8 fluid ounces per gallon |
| Reducer | M650-1057; 10% max |
| Retarder | M650-1057; 10% max |
| AirDry | To touch: 15 min; To handle: 45 min; To recoat: 1 hour |
| Oven Dry | User specific |
| Shelf-Life (Unopened) | 36 months |
| Pot-Life (Catalyzed) | 8 to 12 hours |
| Recoat Instruction | Dry1- 2 hours, scuff with 320 grit & recoat within 4 hours of applicaton of previous coat |
| PH | N/A |

DIRECTIONS:

Stir thoroughly before catalyzing and use. Catalyze Ultra® Flo Clear Conversion Varnish (M615-21XX) with 8 fl. oz. per gallon of Conversion Varnish Catalyst (M615-701). Only catalyze the amount of product needed because excess material cannot be saved. Stir material while adding Catalyst and continue to stir until thoroughly mixed. Allow material to sit for 15 minutes before spraying. Apply in light, even coats of no more than 3-4 wet mils per coat. Additional coats should be applied within 4 hours of previous coat. Scuff sand with 320 grit steared sandpaper between coats. Total dry film thickness of the entire system, including sealers should not exceed 4 dry mil. If a retarder is necessary, use Mohawk Conversion Varnish Reducer/Retarder (M650-1057). NOTES: Total dry film of the entire system should not exceed 4 dry mil. All products should be stirred properly before being used and also continuously agitated while in use to insure product consistency from start to finish. Filtering at every opportunity is suggested. The system should be pre-tested on the wood to be finished under application conditions. Mixing with other products or finish systems is not recommended. Mohawk Finishing Products will not be held liable for finish failure resulting from mixing products or systems. This product is formulated for interior applications and is not recommended or tested for exterior use. Ultra® Flo Clear Conversion Varnish (M615-21XX) is manufactured at spray viscosity. Mohawk Conversion Varnish Reducer/Retarder (M650-1057) is recommended for equipment clean-up. If second coat of Ultra® Flo Clear Conversion Varnish (M615-21XX) cannot be applied within 4 hours after first coat, allow to dry 24 hours, scuff sand surface just prior to recoating with 320 grit steared sandpaper and remove sanding dust. Heavy sanding of previous coats should be avoided. Stainless steel spray equipment is recommended to avoid iron contamination (discoloration). Pot life is approximately 12 hours. Flush equipment and fluid lines at the end of each day with Mohawk Conversion Varnish Reducer/Retarder (M650-1057).

The data on this sheet are calculated values (as formulated) and will not represent exact values for every product. For Safety and Other Precautions, read the SDS before using the product. SDS are available upon request. If Safety Data Sheet is required, contact: Mohawk Finishing Products, a Division of RPM Wood Finishes Group, Inc.; P.O. Box 22000 Hickory, NC 28603; Phone: 1-800-545-0047; Fax: 1-800-721-1545.

Drying times and viscosities reported are as tested under laboratory conditions (77°F (25°C)) with relative humidity of approximately 45%. Changes in temperature and humidity will affect product data.

It is the user's responsibility to verify product compliance with all applicable regulations or permits before proceeding with use. Always pretest any finishing products to verify suitability to the desired use before proceeding with any application. Manufacturer makes no warranties, express or implied, including (but not limited to) warranties of merchantability and fitness for particular purposes. Manufacturer will not be liable for any incidental, consequential or special damages or losses derived, directly or indirectly, from or as a consequence of purchaser's use of this product.

TDS. Mohawk Finishing Products, Division of RPM Wood Finishes Group, Inc. All rights reserved.