



SCRATCH & MAR RESISTER POLISH-CLEAR 2 OZ

TECHNICAL DATA SHEET

PRODUCT NUMBER

DESCRIPTION

M811-0002,M811-0003,M811-0004,M811-0005,M811-0007 SCRATCH & MAR RESISTER POLISH-CLEAR 2 OZ

PRODUCT DESCRIPTION:

Mohawk Scratch & Mar Resister Polish is designed to make finished wood surfaces more resistant to scratches and marring than an untreated surface by adding surface lubrication. Mohawk Scratch & Mar Resister Polish reduces printing of the surface, packing marks and will not affect the finish sheen.

ADVANTAGES:

1. Provides scratch resistance to wood
2. Reduces coefficient of friction by adding surface lubrication
3. Natural and tinted formulas, for light and dark finishes
4. Contains an anti-static agent
5. Scratch & Mar Resister Polish can be recoated
6. Does not affect the sheen
7. Freeze thaw stable

PHYSICAL PROPERTIES AND SPECIFICATIONS

Technology	N/A
Color	N/A
Sheen	N/A
Viscosity	N/A
WPG	8.340808496 lbs/gal
Solids by Volume	0.745424539 ±1%
Solids by Weight	0.752031007 ±1%
Flash Point	200.000000000 °F
HMIS	H: 2, F: 1, R: 0, P: X
Coating VOC (g/l)	245.688120396 g/l
Coating VOC (Lb/Gal)	2.050374046 lbs/gal
Material VOC (g/l)	2.618428286 g/l
Material VOC (Lb/Gal)	0.021851921 lbs/gal
#VOC/#Solid	0.348373988 lbs/lbs solid
VHAP Ratio (#VHAP/#Solid)	0.000000000
Spread Rate	11.956609606 sq. ft./gal @ 1.0 mil DFT (no loss)
Catalyst/Ratio	N/A
Reducer	N/A
Retarder	N/A
AirDry	N/A
Oven Dry	N/A
Shelf-Life (Unopened)	12 months
Pot-Life (Catalyzed)	N/A

Recoat Instruction	N/A
PH	6

Water - CAS 7732-18-5 - solvent
Proprietary Resin - CAS Not Available - resin
1-Propanaminium, 3-(dodecyloxy)-2-hydroxy-N,N-bis(2-hydroxyethyl)-N-methyl-, methyl sulfate (salt) -CAS 18602-17-0 - anti-static
Proprietary Fragrance - CAS Not Available - fragrance
Proprietary Defoamer - CAS Not Available - defoamer

DIRECTIONS:

Before applying Mohawk Scratch & Mar Resister Polish, clean the surface with Mohawk Quick Clean (M107-3012) to remove prior waxes, polishes or other surface contaminants. Spray Mohawk Scratch & Mar Resister Polish directly on the wood surface and wipe dry with a clean cotton cloth. For best results, clean with Mohawk Quick Clean before recoating surface with lacquer or finish. Reapply every 2-4 weeks depending on usage or as needed.

The data on this sheet are calculated values (as formulated) and will not represent exact values for every product. For Safety and Other Precautions, read the SDS before using the product. SDS are available upon request. If Safety Data Sheet is required, contact: Mohawk Finishing Products, a Division of RPM Industrial Coatings Group, Inc.; 3194 B Hickory Blvd, Hudson, NC 28638; Phone: 1-800-545-0047; Fax: 1-800-721-1545.

Drying times and viscosities reported are as tested under laboratory conditions (77°F (25°C)) with relative humidity of approximately 45%. Changes in temperature and humidity will affect product data.

It is the user's responsibility to verify product compliance with all applicable regulations or permits before proceeding with use. Always pretest any finishing products to verify suitability to the desired use before proceeding with any application. Manufacturer makes no warranties, express or implied, including (but not limited to) warranties of merchantability and fitness for particular purposes. Manufacturer will not be liable for any incidental, consequential or special damages or losses derived, directly or indirectly, from or as a consequence of purchaser's use of this product.

TDS. Mohawk Finishing Products, Division of RPM Wood Finishes Group, Inc. All rights reserved.